



THINK FORWARD. FEEL BETTER.

TECAWORK® ECOGREEN® EG 317 – 215 G/M²

SUSTAINABILITY ON ANY BUDGET

Tecawork[®] Ecogreen[®] EG317 offers a sustainable workwear option that fits any budget thanks to a blend of recycled polyester from PET bottles and ethically sourced¹ cotton fibres, achieving a range of sustainability standards.

ROBUST DURABILITY

Founded on the trusted performance of the Tecawork® brand, this fabric is fitted for harsh environments thanks to its strength and abrasion resistance – delivering extended garment life cycles.

BUILT FOR INDUSTRIAL LAUNDRIES

Engineered to retain its shape and looks through the rigours of high-temperature industrial laundering, this fabric prioritises longevity for a cost-effective and sustainability-minded approach.



made for life

TECAWORK® Ecogreen®



| TECHNICAL DATA* | TECAWORK® ECOGREEN® | TEST METHOD |
|-----------------------|---------------------------------|--|
| Quality | EG 317 | |
| Width | 153 cm (+2/-1 cm)* | ISO 22198: 2006 |
| Weight | 215 g/m² (± 5%) | ISO 3801: 1977 |
| Composition | 65/35% rPes/Cotton | ISO 1833: 2020 |
| Construction | Twill 2/1 S | ISO 3572: 1976 |
| Available finishes | Easy Care | |
| | | |
| Physical performance | | |
| Tensile strength | 1200 N x 800 N (± 10%)* | NEN-EN-ISO 13934-1: 2013 |
| Pilling | 4* | ISO 12945-2: 2020 (5000 Rubs) After 5x cleaning cycles at 75°C ISO 15797: 2018 |
| Dimensional change | Max. ± 2 % | NEN-EN-ISO 5077: 2008 After 5x cleaning cycles at 75°C ISO 15797: 2018 |
| Tear strength | 35 N x 30 N (± 10%) | NEN-EN-ISO 13937-1: 2000 |
| | | |
| Care labelling | | |
| Domestic laundering | ₩ P | NEN-EN-ISO 6330: 2012 |
| Industrial laundering | ISO 15797, 75°C: 2018 White: | Visit our website for the laundering recommendations www.tencatefabrics.com Qualification label - ISO 30023 |
| | | |


CERTIFICATION Certification and verification in progress for OEKO-TEX® STANDARD 100, class II Centexbel; 2207156 the following programs:

* All values subject to final certification and specification

|||||||

ETSA

OEKO TEX®







All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.

STeP

20000912 Centexbel

S0 9001